

PRESS-FIT DIODE HAVING A SILVER-PLATED WIRE TERMINATION

~~Background Information~~ Field Of The Invention

The present invention relates to a press-fit diode ~~as recited in the preamble of Claim 1,~~ and a method for manufacturing such a press-fit diode ~~as recited in the preamble of Claim 5.~~

5 Background Information

The design of medium- and high-performance diodes as press-fit diodes is known in the art. Such diodes are used primarily in rectifier applications, and are an important component of bridge rectifiers for today's motor vehicle generators.

10 Known rectifier diodes ~~essentially include~~ a base contact which forms a first terminal of the press-fit diode, a wire contact which forms the second terminal of the press-fit diode, and the actual diode semiconductor chip which is soldered in between the contacts. The base contact is used for pressing the diode into a recess in
15 a substrate element. A printed circuit board, for example, may be soldered to the wire contact.

Figure 1 shows a press-fit diode known ~~from~~ in the ~~related~~ art, having a base contact 3, a diode chip 7, and a wire contact 2. As can be seen, base contact 3 has a wider press-in section which at
20 the same time produces a thermal and electrical connection with the substrate element. Diode chip 7 is attached by, for example, soldering or welding between base contact 3 and wire contact 2. The particular solder layers are designated by reference numeral 8.

25 Wire contact 2 includes a broadened wire head 5 for attaching diode chip 7, and a narrower wire shaft 4 which is externally accessible.

For a motor vehicle generator, for example, wire shaft 4 is connected to one phase of the stator windings.

Both base contact 3 and wire contact 2 are usually made of copper and plated with a nickel layer 6, which in particular is used as a corrosion barrier between the copper and the material of the substrate element (usually e.g., aluminum). Press-fit diode 1 is further encased by a plastic sheathing 9.

As mentioned, wire contact 2 may be attached to a printed circuit board by either soldering or welding. If the wire contact is soldered, the entire metal surface of diode 1 is electroplated with tin. Tin plating is usually performed using a drum tin plating process in which press-fit diodes 1 are electroplated in bulk. This process is particularly simple and economical.

However, for operation under severe environmental conditions, such as in a motor vehicle, for example, problems often arise for tin-plated press-fit diodes+, such as the problems recited below.

Severe temperature fluctuations and vibratory stress in the rectifier of a motor vehicle generator result in micromotions between the tin surface of the base contact and the wall of the substrate element into which the diode is pressed. The use of aluminum cooling plates as substrate elements thus causes fretting corrosion, on account of which high contact resistance is ~~observed~~ results, which may in turn result in overheating and failure of press-fit diode 1.

~~The~~An object of the present invention, therefore, is to provide a press-fit diode, and a method for manufacturing a press-fit diode, which is less susceptible to fretting corrosion of the base contact, and whose wire contact has an easily solderable surface. Furthermore, the press-fit diode should be as economical as possible to manufacture.

~~This object is achieved according to the present invention by the features recited in both Claim 1 and Claim 5. Further embodiments of the present invention are the object of the subclaims.~~

Summary

5 ~~An essential aspect of~~ In accordance with the present invention ~~is that,~~ the wire contact for the press-fit diode is provided at least partially with a surface layer of silver, and the base contact is produced from a material or provided with a metal layer which causes the least possible amount of corrosion of the material of
10 the substrate element. Silver plating has particularly good soldering characteristics, and in addition has a melting point over a temperature of approximately 300°C, which arises during the manufacturing of the press-fit diode, for example, when the diode chip is soldered in between the base contact and the wire contact,
15 or when the sheathing is cured. Silver is therefore preferred over other possible materials.

Because of the great difference in electrochemical potential with respect to aluminum, the base contact is ~~preferably not~~ silver-plated, and is provided with a nickel layer, for example.
20 Nickel is much less noble than silver, and therefore has less of a tendency toward corrosion with aluminum. The disadvantage of different surface coatings for the base contact and the wire contact, however, is that it is not possible to silver-plate the press-fit diode in the economical bulk process.

25 Therefore, the wire contacts are ~~preferably silver-plated~~ individually (before the press-fit diode is assembled).
~~Preferably~~In an example embodiment, not the entire wire contact but only a portion thereof is silver-plated. According to one ~~preferred example~~ embodiment of the present invention, a section
30 of the wire contact used for attaching the diode chip is not provided with the silver layer. Completely silver-plating the wire contact is usually disadvantageous, since the silver forms an alloy

with the solder used for soldering the diode chip, the melting point of the alloy being too low for further processing of the press-fit diode, such as the sheathing with plastic, for example. For this reason the region for attaching the diode chip ~~is preferably~~may
5 be recessed.

For manufacturing the partially silver-plated wire contacts, the wire contacts are, for example, inserted in a rack with the wire shafts pointing downward, and the wire shafts are immersed in an electroplating vat.

10 ~~The present invention is explained in greater detail below, with reference to the appended drawings.~~

Brief Description of the Drawings

Figure 1 shows a conventional press-fit diode known ~~from~~in the related art.

15 Figure 2 shows a press-fit diode having silver plating according to a first example embodiment of the present invention.

Figure 3 shows a wire contact having a partial silver plating, ~~and.~~

Figure 4 shows a press-fit diode having a partially silver-plated wire contact and a base contact which is not
20 silver-plated.

Detailed Description

~~With regard to the explanation of Figure 1, reference is made to the introductory description.~~

Figure 2 shows a press-fit diode, whose contacts are provided with
25 an additional silver layer 10. Press-fit diode 1 essentially includes a base contact 3, a wire contact 2, and ~~the actual~~a diode semiconductor chip 7 which is soldered in between contacts 2 and 3. The solder layer is designated by reference numeral 8.

Base contact 3 includes a broadened section for pressing into a substrate element, such as an aluminum plate, for example. At the same time, pressing in produces a durable thermal and electrical contact.

- 5 Wire contact 2 includes a wire head 5 which is used for connecting to diode chip 7, and a wire shaft 4 by which press-fit diode 1 may be connected to a printed circuit board, for example.

Base contact 3 and wire contact 2 are made of copper which is provided with a nickel layer 6. A central section of press-fit diode
10 1 is sheathed in plastic 9 to protect diode chip 7.

The contact regions protruding from sheathing 9 are provided with a silver layer 10. The nickel layer is used as a diffusion barrier between the copper and the silver layer 10. For production of silver layer 10 the diodes may, for example, be electroplated in bulk in
15 a drum process.

However, when substrate elements made of certain materials, such as aluminum, for example, are used, this example embodiment has the disadvantage that increased corrosion may occur between the silver and the substrate material.

- 20 Another example embodiment of the present invention in which this problem does not occur is illustrated in Figures 3 and 4.

Figure 3 shows a wire contact 2 having a partial silver plating. The silver plating is provided only on wire shaft 4 of wire contact 2, but not on section 5 to which diode chip 7 is attached.

- 25 Such a partially silver-plated wire contact 2 may be manufactured, for example, by inserting wire contacts 2 individually into a rack (with wire shafts 4 pointing downward) and immersing wire shafts 4 in an electroplating vat. Wire contact 2 is then joined to other components 3, 7 and sheathed in plastic 9. Base contact 3 is not
30 silver-plated in this case, and is made of, for example, copper

provided with a nickel layer 6. When a substrate element made of aluminum is used, this results in much less electrolytic corrosion between nickel layer 6 and the aluminum, compared to that between silver layer 10 and aluminum.

- 5 The result is a press-fit diode having a very easily solderable wire contact 2, and a base contact 3 which may be pressed into an aluminum substrate without corrosion problems.

~~List of reference numerals~~

- ~~1 Press fit diode~~
- ~~2 Wire contact~~
- ~~3 Base contact~~
- 5 ~~4 Wire shaft~~
- ~~5 Wire head~~
- ~~6 Nickel layer~~
- ~~7 Diode chip~~
- ~~8 Solder layer~~
- 10 ~~9 Plastic sheathing~~
- ~~10 Silver layer~~

~~Abstract~~

ABSTRACT

A press-fit diode, ~~in particular~~ e.g., for rectifier applications, includes a diode chip ~~(7)~~, a base contact ~~(3)~~ for pressing into a substrate, which base contact forms a first terminal of the
5 press-fit diode ~~(1)~~, and a wire contact ~~(2)~~ which forms a second terminal of the press-fit diode ~~(1)~~. ~~It is possible to manufacture an~~ An easily solderable corrosion-resistant press-fit diode ~~(1)~~ is provided by ~~providing~~ coating the wire contact ~~(2)~~ at least partially with a silver layer ~~(10)~~, the base contact ~~(3)~~ ~~preferably~~
10 having no silver layer ~~(10)~~.

~~Figure 4~~